

Artikelnummer/Article Number: 80420
Kurzbezeichnung/Short Term: EMAIL
Bezeichnung: Haftmittel für ABIGCOLOR
Description: Adhesive for ABIGCOLOR
Warengruppe/Product Group: 80

Verbraucher-Einheit/Cosumer Unit:

EAN-13 Code:

Einzelgewicht/Weight: 0,081 kg

Höhe/Height: mm

Breite/Width: mm

Länge/Length: mm

Marke/Brand: ABIG

Haftmittel für Abigcolor,

Kupferteil mit Schleiffgummi reinigen. Mit hartem Pinsel hauchdünn auftragen und danach Abigcolor in rechtem Winkel aufstreuen.

Vor dem Brennen bei 150°C mindestens eine Stunde trocknen lassen.

Schablonieren: Auf mit Abigcolor vorgebranntem Kupferteil Schablone auflegen, mit Haftmittel hauchdünn betupfen, danach Kontrastfarbe Abigcolor aufstreuen. Schablone entfernen, mindestens eine Stunde trocknen lassen, danach bei 150 °C brennen.

Adhesive for Abigcolor:

Clean the copper piece with sanding rubber. Apply a very thin layer with a hard brush and then sprinkle Abigcolor on at a right angle.

Allow to dry for at least one hour before firing at 150°C.

Stenciling: Place the stencil on the copper part pre-fired with Abigcolor, dab on a very thin layer of adhesive, then sprinkle on the contrasting Abigcolor. Remove the stencil, allow to dry for at least one hour, then fire at 150°C.